## **Technical Data Sheet**



Product 2K Fast DTM Non-Iso Mini Night Flash Topcoat

Codes DTM2083C DTM2083A DTM2083T

Use Top-coat especially for direct to metal applications such as diamond

cut alloy wheels. Has excellent adhesion, long pot-life and contains no isocyanates

Mix ratio is 1:1:1 DTM2083C:DTM2083A:DTM2083\* by volume.

or 1:1 DTM2083C:DTM2083A + 50% DTM2083T by volume.

For example mixes see below. To achieve the correct finish and gloss it is vitally important to use

the recommended mix ratio. Pot/use life is 7 hours minimum at 20°C.

*Total mixed paint required		90ml	180ml	300ml
	DTM2083C DTM2083A DTM2083T		60ml 60ml 60ml	100ml 100ml 100ml

Preparation Ensure all surfaces to be coated are dry and free from any grease and other

contamination. We strongly advise using Jaytees Preparation Wipe TS0028

Application Shake cans well before use.

Safety

Use conventional spray application.

to a dry film thickness of 20-30 microns in two coats. Flash off for 2 mins between coats.

We recommend a substrate temperature between 15 and 25°C.

Flash off for 5 mins before curing.

Cure Cure for 15-20 mins at 60°C substrate temperature.

IR Curing: 10-15 mins minimum @20cm distance using 1KW lamp. Allow to cool to

ambient temperarure before exposing to external enviroment.

Coverage 12.1m<sup>2</sup> per mixed litre (assuming 100% transfer efficiency) @25 micron dry film thickness

Health and Always read and understand the appropriate MSDS before proceeding.

Store in cool dry cconditions in original packaging. When not in use keep lids tightly closed

Always check colour and finish before proceeding. Jaytees strive to ensure all information about the product is correct however we have no control over application conditions or equipment. Therefore we cannot accept liability for the performance of the product in service or any loss or damage arising out of use unless agreed in writing prior to use.

12.7.24

REV 0